



GC1 IVORY

Basis Weight g/m ² ±3%	Thickness µm (±4%)	Stiffness (Taber 15°) mN·m (+0/-20%)	
		CD	MD
215	305	4.2	8.6
235	355	5.3	10.8
250	380	7.3	14.1
270	410	8.8	17.4
295	460	11.9	24.6
325	510	15.9	31.2
350	560	18.5	38.3
380	610	21.8	43.8

Property	Unit	Value
PPS (Top)	µm	1.4±0.3
Moisture	%	6.0 ±1.0
Brightness (Top)	%	91.5±2
75°Gloss(Top)	%	50±5
IGT Blister(Top)	m/s	• 4.2
COBB Test(60s) (Top)	g/m ²	40±15
PLY Bonding	J/m ²	• 430

Test condition (ISO): temp 23±1°C, relative humidity 50±2%

Note: Shaded substances are non-regular substances which are not produced regularly.