

TECHNICAL DATA SHEET



OWV Shot Line

series 2000

| Item | Description | Specification |
|------------------------------------|---|--|
| Front Layer PVC | Туре | Monomeric PVC film |
| | Thickness | 140 ± 10 micron |
| | Front Color | White |
| | Back | Black full coated |
| | Shrinkage | ≤ 3 mm |
| | Surface tension | ≥ 30 dyne / cm |
| | Holes No. | Average 130 / sq inch |
| | Hole Diameter | 1.6 mm |
| | Distance Between Holes | 2.4 mm |
| | Hole Space (transparency) | 40% |
| | Opacity | 98% |
| Adhesive | Туре | Clear removable (solvent based pressure sensitive glue) |
| | Thickness | 25 ± 3 micron |
| | Application conditions | 15°C~40°C (thermal range), ≥8°C min. application temperature |
| | Initial Adhesion-Ball Tack | ≥5 Steel Ball (GB4852-84/ CNS) |
| | Peeling force | (24 hours) 5 ≤ x ≤ 10 N/25 mm |
| | Expected lifetime | 8 months. Six months for a clean removal. Adhesion may increase with |
| | | time. |
| | | Max one year cleanly removable at the temperature of 18-25°C and RH of |
| | Removable Durability | 50-60% (provided that the glass surface is very clean when sticking). |
| Liner | - | DE |
| | Туре | PE coated kraft paper White |
| | Color | - 17 |
| | Weight Release Force | $140 \text{ g} \pm 5 \text{ g/m}^{2}$ 0.03 N/4cm |
| C' 'l. l. l | | · |
| Sizes available | Meter x Meter | 1,37 x 50 |
| Storage Period | 12/15 months under ordinary condition at the average temperature of 22°C and relative humidity of 50-55%. | |
| Applications | Outdoor digital printing and screen printing one way vision media for signage display, shop window advertising, vehicle graphic, subway and building glass walls. | |
| Compatibility of machines and inks | Media is suitable for all solvent and eco-solvent digital printers with cold or heating system applications. All tests are made with the original printer manufacturers inks (Roland, Mimaki, Scitex, Vutek, HP). | |
| Safety Caution | REACH - Complying with the Italian Decree-Law nbr. 133 issued on 14.09.2009 published on the Italian Gazzetta Ufficiale, we inform that the substance Bis(2-ethyl(hexyl)phthalate (DEHP) is present in a concentration of 0,13%. For further information, please refer to the certified copy available of the analyses worked out on the substances taken into consideration by REACH (Registration Evaluation Authorization of CHemicals). ROHS - Cadmium free. | |
| Notes | Published information is based upon research and information which the Company believes to be reliable although such information does not constitute a warranty. Because of the variety of uses of the products and the continuing development of new applications, the purchaser should carefully consider the suitability and performance of the product for each intended use, and the purchaser shall assume all risks regarding such use. The seller shall not be liable for damages in excess of the purchase price of the product nor for incidental or consequential damages. All specifications are subject to changes without prior notice. | |

Update: June 2018