

JT 10700 WG-BFG-XR

PRODUCT DESCRIPTION

Highly conformable self-adhesive cast PVC printing media with a repositionable permanent adhesive combined with Bubble-free technology.

Face Material: 50 µm white gloss, cast PVC

Adhesive: Solvent permanent, repositionable, grey tie coat

Liner: PE coated Bubble-free liner, 155g/m²

TYPICAL USE

Long-term applications for demanding corrugations such as full vehicle wrapping and highly conformable 3D surfaces.

Thanks to the repositionable permanent adhesive combined with the Bubble-free technology, the film is easy to position & reposition during application and ensures entrapped air can easily be squeezed out without the need to puncture the film.

PROCESSING

The face film has been especially developed for exceptional print results on all major printer platforms such as Solvent, Eco-Solvent and Latex printing on wide-format printing equipment.

UV printing is also possible as long as the selected inks are flexible enough for the expected deformation. If printed on UV, please adapt your print speed and curing settings.

To achieve optimal protection and durability, JT 10700 Series needs to be laminated with LF 10700 Series.

To achieve the best possible print quality, please make sure that the correct ICC profiles and printer settings are used.

Profiles can be obtained from our subsidiaries or distributors, or can be downloaded from: www.mactacgraphics.eu.

To achieve optimal application performance, please make sure that the media is completely dry.

In case of graphics printed with solvent inks, printed media should be loosely wound on its core, with a maximum length of 5 meters to ensure sufficient drying.

For further information on printing, application and removal, please refer to "TB 4.2 Application Bulletin of JT 10700 Series".

To ensure application suitability, always test the proposed construction under actual application and end-use conditions before going into full production.

SHELF LIFE

2 years when stored at 15 to 25°C and ± 50 % relative humidity (in the original packaging).

PHYSICAL PROPERTIES (TYPICAL VALUES)

Average Values Test Method

Average Values Test Method		
Thickness		
Face (microns)	50 µm	ISO 534
Adhesive data, 23°C (N/25 mm)		
Peel adhesion on stainless steel		
- Quick tack	6.3	FTM9
- 24 hour residence	10.6	FTM1
Dimensional stability		
Elongation	>200%	DIN 53455
Shrinkage (48 hours at 70°C applied on Aluminium)	Max. 0.3 mm	FTM14
Temperature ranges		
Minimum application temperature (°C)	+ 10°C	
Service temperature range (°C)	- 20°C to + 70°C	
Certification		
Fire Classification	B-s1, d0	EN13501-1

EXPECTED DURABILITY

Central Europe Zone 1

Unprocessed	7 years	ISO 4892-2
Printed & laminated*	Up to 5 years	ISO 4892-2

*For more information, refer to "TB 7.5 Outdoor Durability of Mactac Graphics - Self-adhesive films".

Note : Overlamination of the inkjet-printed material delays the eventual colour fading that may occur over time. This colour fading is dependent on the quality of the inkjet inks, the orientation of the printed material, the angle of display and the exact geographical location of exposure.

Exposure to severe temperatures, ultraviolet light, and/or conditions in Southern European countries, tropical, sub-tropical or desert regions will cause more rapid deterioration. This also applies to polluted areas, high altitudes and south-facing exposure. No durability warranty is given for horizontal exposure.

DISCLAIMER

Avery Dennison warrants that its Products meet its specifications. Avery Dennison gives no other express or implied guarantees or warranties with respect to the Products, including, but not limited to, any implied warranties of merchantability, fitness for any particular use and/or non infringement. All Avery Dennison products are sold with the understanding that the purchaser has independently determined the suitability of such products for its purposes. The period of warranty is one (1) year from the date of shipment unless expressly provided otherwise in the product data sheet. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see <http://terms.europe.averydennison.com>. Avery Dennison's aggregate liability to Purchaser, whether for negligence, breach of contract, misrepresentation or otherwise, shall in no circumstances exceed the price of the defective, non-conforming, damaged or undelivered Products which give rise to such liability as determined by net price invoices to Purchaser in respect of any occurrence or series of occurrences. In no circumstances shall Avery Dennison be liable to Purchaser for any indirect, incidental or consequential loss, damage or injury, including without limitation, loss of anticipated profits, goodwill, reputation, or losses or expenses resulting from third party claims.